

3015 Cavity Wax


Anti corrosion wax coating to protect inside spaces of car bodyworks such as insides of doors, side panels, motor hoods and chassis bars.

- Non-drying coating on metals with long term corrosion protection
- Resistant to salt, moisture and general corrosive atmosphere
- Strong penetration so that difficult accessible parts of the bodywork can be conserved
- Non aggressive to plastics, rubbers, and paints

Substrate preparation

Surface must be dry and clean, free from dirt, rust and grease.

Mixing ratio



The product is ready to use!
Shake the product well before use!

Application



Number of layers:	1
Recommended layer thickness (wet):	200 µm
Recommended layer thickness (dry):	100 µm
Temperature range:	apply between 10 °C and 25 °C (50 - 77 °F)



Use on room temperature.
Shake or stir before use.
Surface must be dry and clean, free from dirt, rust, grease etc.
Spray or brush an even layer on the object or surface to be coated.
Leave to evaporate/dry.
Do not spray on the exhaust, brake systems, or on motor parts.
Can be removed with aromatic solvents as white spirit, boiling point naphtha, xylene, etc

Drying

3015 Cavity Wax



100 micron wet layer/20°C and ventilation

Dust dry	2 h
Trough dry	24 h

Storage

Cool (10°C - 20°C) and dry.

Physical properties

Density / weight: 0.865 kg/L
Coverage: 1L/5m²
Operating temperature: -30 - 80°C
Peak temperature: 110°C
Viscosity (DIN CUP 4mm): 50 s

Testing of material

Any kind of testing of the applied material (adhesion test, stone-chip test, chemical resistance, salt chamber test ...) has to be done at least 15 days after the application.

Packaging

Product number	Description	Volume/Weight	Packaging
3015-1	Transparent	1 L	12

Shelf life

12 months from the production date under normal storage conditions and unopened can.

Additional information

FOR PROFESSIONAL USE ONLY!

Always read the instructions.

IMPORTANT: This product contains hazardous substances at work so it is necessary to always use/wear appropriate protective equipment. For further instructions, check the label on the product and safety data sheet. A person who uses the product for any purpose other than recommended in this technical data sheet, acts at his own risk. It is the user's responsibility to take all necessary steps to fulfil the local legislation.

Materials described are designed for application by professional, trained personnel using proper equipment and are not intended for sale to the general public.



Technical data sheet

2024-1

3015 Cavity Wax

Information and methods described are based on the best information and practices known to us and serve merely as guidelines for optimal use, without liability to performance, results or fitness for any intended use. We do not accept any responsibility for the behaviour of the product or damage arising from the use of the product. Before using the product, the user must check if this is the latest version.

All products mentioned in this data sheet are trademarks owned by Silco.